

Hakizimana T4.

Table 4. LLIN durability associated with fabric integrity.

cell	Cyimo	Rusheshe	Bungwe	Bushenya	Rutabo	Burima
LLIN type	p-ester	p-ethylene	p-ester	p-ethylene	p-ester	p-ethylene
T₀						
good	100	100	100	100	100	100
serviceable	0	0	0	0	0	0
replace	0	0	0	0	0	0
T₁₂						
good	47	20	67	37	27	60
serviceable	20	43	13	13	37	27
replace	33	37	20	50	13	13
T₂₄						
good	10	3	3	3	10	6
serviceable	27	7	47	50	37	47
replace	63	90	50	47	53	47

* estimated % associated with threepHI-related conditions: pHI<64 - 'good', 64<pHI<768 - 'serviceable', pHI>768 - 'replace'